

Honeywell Titan[®] 8422

Polymers for Asphalt

Honeywell Titan 8422 is a polyolefin used to modify asphalt for roofing application.

Typical Properties:

Property	Value
Hardness (ASTM D-5)	< 1 dmm
Drop Point, Mettler (ASTM D-3954)	115°C (239°F)
Viscosity @ 140°C (284°F) Brookfield	450 cps

Product form and packaging:

Property	Value
Product Form	Free flow prill

Safety Precautions

Consult our Material Safety Data Sheet for specific recommendations on safe handling.

For additional information or to contact us, please visit: www.honeywell-additives.com

Honeywell Corporate Headquarters

101 Columbia Road
Morristown, NJ 07962
Tech Assistance: 973-455-5382
Customer Service: 973-455-2145
Toll Free in U.S.:
Tech Assistance: 800-451-9961
Customer Service: 888-245-4738

Asia / Pacific Honeywell

No.430, Li Bing Road,
Zhangjiang
Hi-Tech Zone, Shanghai
201203
China
Telephone: +8621 2894-2000
Fax: +8621 5855-3543

Europe / Middle East / Africa

Honeywell Belgium N.V.
Interleuvenlaan 15i
3001 Heverlee, Belgium
Telephone: +32 16 39 12 11
Fax: +32 16 40 00 33

Honeywell International (I) Pvt Ltd

6th Floor, Tower B, Building No.9
DLF Cyber City, Phase III
Gurgaon-122002
Haryana
India
Telephone: +91-124-4031361-65

DISCLAIMER: Although all statements and information contained herein are believed to be accurate and reliable, they are presented without guarantee or warranty of any kind, express or implied. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liability for use of the information and results obtained. Statements or suggestions concerning the use of materials and processes are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all toxicity data and safety measures are indicated herein or that other measures may not be required.

Honeywell

© 2014 Honeywell International Inc.
All rights reserved