NduroMatt™ X302

Polyethylene based matting agent for solvent and water-borne coatings. Typical loadings levels are 1 – 6 % by weight. Fast incorporation and addition flexibility – from grind step to post-addition.

Typical Properties:

Property	Value
Hardness, dmm	< 0.5 dmm
Drop Point, Mettler	134 - 140°C (273 - 284 °F)
Density @ 23°C	0.985 – 0.995
Acid Number	< 40 mg KOH/g

Product Form and Size

Property	Value
Product Form	Micronized Powder
Mean Value	4 – 8 microns

Safety Precautions

Consult our Safety Data Sheet for specific recommendations on safe handling.

For additional information or to contact us, please visit: www.honeywell-additives.com

Honeywell Corporate Headquarters 115 Tabor Road Morris Plains, NJ 07950 Tech Assistance: 973-455-5382

Toll Free in U.S.:

Tech Assistance: 800-451-9961 Customer Service: 888-245-4738 Asia / Pacific Honeywell No.430, Li Bing Road,

Zhangjiang Hi-Tech Zone, Shanghai

201203 China

Telephone: +8621 2894-2000 Fax: +8621 5855-3543

Europe / Middle East / Africa

Honeywell Belgium N.V. Gaston Geenslaan 14 3001 Heverlee

Belgium Telephone: +32 16 39 12 11

Fax: +32 16 39 13 71

Honeywell International (I) Pvt Ltd

6th Floor, Tower B, Building No.9 DLF Cyber City, Phase III Gurgaon-122002

Haryana India

Telephone: +91-124-4031361-65

DISCLAIMER: Although all statements and information contained herein are believed to be accurate and reliable, they are presented without guarantee or warranty of any kind, express or implied. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liability for use of the information and results obtained. Statements or suggestions concerning the use of materials and processes are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all toxicity data and safety measures are indicated herein or that other measures may not be required.

