

ACumist® A-6

Small particle size Oxidized high density Polyethylene available for water or solvent based thin film applications. Excellent slip, and abrasion resistance., Used in flexographic inks, wood and industrial coatings applications

TYPICAL PROPERTIES

Property	Value
Hardness	<0.5
Drop Point, Mettler	137°C (279°F)
Density	0.99
Acid Number	26 to 40

REGULATORY APPROVALS

Property	Value
Plastic Pipe Institute/NSF*	No
FDA Indirect Approvals*	Yes

PRODUCT FORM AND SIZE

Property	Value
Product Form	Micronized powder
Size	6.0 to 7.5

DISCLAIMER: Although all statements and information contained herein are believed to be accurate and reliable, they are presented without guarantee or warranty of any kind, express or implied. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liability for use of the information and results obtained. Statements or suggestions concerning the use of materials and processes are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all toxicity data and safety measures are indicated herein or that other measures may not be required.

© 2021 Honeywell International Inc.

All rights reserved

