

## TIP5000

# Thermal Insulator Pad with High Thermal Conductivity

### BENEFITS AND FEATURES

- High thermal performance
- High breakdown voltage
- Good resistant to tears, cut-throughs and punctures
- Single side PSA available for easy assembly

### OVERVIEW

Honeywell TIP5000 thermal insulator is designed to provide low thermal impedance and high isolation for high power and high voltage applications. Integrated fiberglass reinforcement protects the pad from tears, cut-throughs and punctures. It is designed to have smooth and conformal surface which provide excellent mating under low pressure mounting. Offered in thicknesses ranging from 0.25 mm to 0.50mm.

### TYPICAL APPLICATIONS

- Automotive electronics
- Power conversion equipment
- Power supply equipment
- Motor controllers
- Speaker amplifier
- Power switch

### Storage & Use

- Shelf Life 12 months at 23±2°C

Property	TIP5000	Test Method
Color	White	Visual
Thickness (mm)	0.25-0.50	ASTM D374
Specific Gravity	2.5	ASTM D792
Hardness (ShoreA)	90	ASTM D2240
Thermal Conductivity (W/m·K)	5.0	Hot Disk
Thermal Impedance (°C-in <sup>2</sup> /W)	0.18	ASTM D5470 (@10psi)
	0.15	ASTM D5470 (@50psi)
Breakdown Voltage (Vac)	>4,500	ASTM D149
Dielectric Constant@1MHz	3.5	ASTM D150
Volume Resistivity (Ohm-cm)	5x 10 <sup>13</sup>	ASTM D257

### Honeywell Electronic Materials

USA: 1-509-252-2102  
 China: 400-840-2233  
 Germany: 49-5137-999-9199  
 Japan: 81-3-6730-7092  
 Korea: 82-2-3483-5076  
 Singapore: 65-6580-3593

[www.electronicmaterials.com](http://www.electronicmaterials.com)

Although all statements and information contained herein are believed to be accurate and reliable, they are presented without guarantee or warranty of any kind, express or implied. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liability for use of the information and results obtained. Statements or suggestions concerning the use of materials and processes are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all toxicity data and safety measures are indicated herein or that other measures may not be required.

DS.0318Rev2  
 ©2020 Honeywell International Inc.