

HONEYWELL ACLAR[®] SupRx 900

Aclar[®] SupRx 900 is a high transparent 0.9 mil (23 µm) PCTFE homopolymer high moisture barrier film designed for semi-rigid and flexible film packaging applications for highly sensitive medicinal products in pharmaceutical and medical markets. This film is suitable for thermoforming and lamination to various substrates including PVC and PVC free solutions, such as PET, PP, and PE substrates for environmentally friendly applications.

PROPERTIES OF 0.90 MIL (23µm) FILM AT 73°F (23°C) - 50% RH	TYPICAL VALUE		TEST METHOD	
	ENGLISH	METRIC		
Specific Gravity		2.11 g/cm ³	ASTM D1505	
Yield	14,595 in ² /lb.	20.75 m ² /kg		
Haze	< 1 %		ASTM D1003	
Crystalline Melting Point	412°F	211°C	ASTM D4591	
Dimensional Stability (10 mins. @ 300°F/149°C)	- MD - TD	≤ + 15 % < - 13 %	ASTM D1204	
Tensile Strength	- MD - TD	11,000 – 16,000 psi 6,000 – 7,200 psi	76 - 110 MPa 41 - 55 MPa	ASTM D882
Elongation	- MD - TD	100 - 150 % 200 - 275 %		ASTM D882
Modulus, secant	- MD - TD	190,000 - 225,000 psi 165,000 - 210,000 psi	1310 - 1551 MPa 1138 - 1448 MPa	ASTM D882
Surface Tension (treated side)		≥ 42 dynes/cm	ASTM D2578	
Oxygen Transmission Rate @ 73.4°F (23°C) / 50% RH		cc/100in ² dbar 5.55	cc/m ² dbar 86.09	ASTM F1927-20
Water Vapor Transmission Rate @ 77°F (25°C) / 60% RH @ 86°F (30°C) / 65% RH @ 104°F (40°C) / 75% RH @ 100°F (37.8°C) / 100% RH		g/100in ² d 0.0018 0.0038 0.0130 0.0170	g/m ² d 0.028 0.059 0.202 0.264	ASTM F1249

Please refer to the Honeywell Regulatory Clearance Certificate (RCC) for compliance status.



All statements and information provided herein are believed to be accurate and reliable, but are presented without guarantee, warranty or responsibility of any kind, express or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated herein, or that other measures may not be required. User assumes all liability for use of the information and results obtained. Aclar[®] is a registered trademark of Honeywell International.

For more information:

To learn more about Honeywell Aclar Film, visit advancedmaterials.honeywell.com or contact your Honeywell account manager.

Honeywell

115 Tabor Road
Morris Plains, NJ 07950
1-800-631-8138
www.honeywell.com

TCS-24-16-EN | 05/24
© 2024 Honeywell International Inc.

THE
FUTURE
IS
WHAT
WE
MAKE IT

Honeywell