

# Honeywell Spectra® Fiber

## PHYSICAL PROPERTIES (nominal)

Product Family	Spectra® fiber	Weight/ Unit Length (denier) / (decitex)	Ultimate Tensile Strength (g/den) / (Gpa)	Modulus (g/den) / (Gpa)	Elongation (%)	Breaking Strength (lbs)	Density (g/cc) / (lbs/in <sup>3</sup> )	Filament Tow	Filament (dpf)
HT	240	267	41	1350-1650	3.1-3.5	22	.97	60	4
	300	333	39.5	1200-1500	2.9-3.7	26	.97	60	5
	375	417	45	1300-1700	2.9-3.6	38	.97	120	3.1
S-900	650-926	650 / 722	30.5 / 2.61	920 / 79	3.6	44	0.97 / 0.035	60	10.8
	1200	1200 / 1333	30 / 2.57	850 / 73	3.9	79	0.97 / 0.035	120	10.0
	2400	2400 / 2667	29.5 / 2.53	915 / 78	3.9	157.7	0.97 / 0.035	240	10.0
	4800	4800 / 5333	26.5 / 2.27	885 / 76	3.6	281	0.97 / 0.035	480	10.0
	5600	5600 / 6222	25.5 / 2.18	775 / 66	3.5	315	0.97 / 0.035	480	11.7
S-1000	75	75 / 83	43 / 3.68	1550 / 133	2.9	7	0.97 / 0.035	40	1.9
	100	100 / 111	40.5 / 3.47	1580 / 135	2.9	9	0.97 / 0.035	40	2.5
	130	130 / 144	38 / 3.25	1390 / 113	3.2	11.1	0.97 / 0.035	40	3.3
	180	180 / 200	38 / 3.25	1310 / 112	3.3	15.1	0.97 / 0.035	60	3.0
	200	210 / 233	38 / 3.25	1160 / 90	3.5	17.9	0.97 / 0.035	82	2.5
	215	215 / 239	38 / 3.25	1320 / 113	2.9	18	0.97 / 0.035	60	3.6
	275	275 / 306	36 / 3.08	1320 / 113	3.1	22	0.97 / 0.035	60	4.6
	375-133	375 / 417	35 / 3.00	1200 / 103	3.1	29	0.97 / 0.035	60	6.3
	375-189	375 / 417	35 / 3.00	1200 / 103	3.1	29	0.97 / 0.035	60	6.3
	400	409 / 454	36 / 3.08	1090 / 93	3.4	33.5	0.97 / 0.035	164	2.5
	435-145	435 / 483	37.5 / 3.21	1260 / 108	3.3	36	0.97 / 0.035	120	3.6
	435-195	435 / 483	37.5 / 3.21	1260 / 108	3.3	36	0.97 / 0.035	120	3.6
	650-115	650 / 722	36 / 3.08	1175 / 101	3.3	52	0.97 / 0.035	120	5.4
	1300-143	1300 / 1444	37.5 / 3.21	1345 / 115	3.3	107.5	0.97 / 0.035	240	5.4
	1300-159	1300 / 1444	35.5 / 3.04	1300 / 111	3.3	101.7	0.97 / 0.035	240	5.4
	1600-180	1600 / 1779	38 / 3.25	1380 / 118	3.3	135	0.97 / 0.035	360	4.4
	2600	2600 / 2889	34 / 2.91	1135 / 97	3.5	195	0.97 / 0.035	480	5.4

**DISCLAIMER:** Although all statements and information contained herein are believed to be accurate and reliable, they are presented without guarantee or warranty of any kind, express or implied. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liability for use of the information and results obtained. Statements or suggestions concerning the use of materials and processes are made without representation or warranty that any such use is

free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all toxicity data and safety measures are indicated herein or that other measures may not be required.

© 2013 Honeywell International Inc. All rights reserved